

# Analysis Report

**Product Type:** MDF samples  
**Sample from:** Alfawood Pindos  
**Income date:** 08/06/2018  
**ID Number:** 5107 - 5108 - 5109  
**Remarks:** EN ISO 12460-5:2015 (perforator)

## RESULTS

s/n Properties	ID 5107	ID 5107	ID 5108	ID 5108	ID 5109	ID 5109
	MDF 6 mm E0 + Test 1	MDF 6 mm E0 + Test 2	MDF 16 mm E0 + Test 1	MDF 16 mm E0 + Test 2	MDF 19 mm E0 + Test 1	MDF 19 mm E0 + Test 2
1 <b>Moisture content of board (%)</b>	<b>3.81</b>		<b>4.31</b>		<b>4.23</b>	
2 Perforator value (mg/100 gr ODB)	2.13	2.29	2.53	2.63	2.31	2.47
3 <b>Average perforator value (mg/100 gr ODB)</b>	<b>2.21</b>		<b>2.58</b>		<b>2.39</b>	
4 Formaldehyde content @ 6,5% MC/ MDF	3.14	3.37	3.25	3.38	3.00	3.20
5 <b>Average Formaldehyde content @ 6,5% MC/ MDF</b>	<b>3.26</b>		<b>3.32</b>		<b>3.10</b>	